



4915-PMA-85 HIGH SOLIDS SHORT OIL ALKYD

4915-PMA-85 HIGH SOLIDS SHORT OIL ALKYD which is cut to 85% non-volatile in PM Acetate Solvent. This resin has good cure response with melamine/butylated melamine type resins and offers a fast reduction curve in aromatic and oxygenated solvents.

SOLUTION PROPERTIES:

Non-volatile by weight	85 ± 2%
Non-volatile by volume	83 ± 2%
Weight per gallon @ 25°C	9.05 ± 0.2 pounds
Viscosity @ 25°C	Z ₂ – Z ₄
Flash Point (Seta)	116°F
Color, Gardner	8 maximum
Solvent	PM Acetate
Cure Type	Baking

SOLID RESIN PROPERTIES:

Phthalic Anhydride	Present
Oil Type	TOFA
Oil Length	Short
Acid Value	10 Maximum
Modifier	None
OH Equivalent Weight	375

DRIER RECOMMENDATION (% METAL BASED ON RESIN SOLIDS):

None recommended.

April 2019

While the information contained herein is deemed accurate, it is intended as a guide only and property values and ranges listed above should be regarded as typical values and should not be construed either as a product specification or as a guaranteed analysis for any specific lot of the product. All guarantees/warranties and other terms existing are exclusively contained in the Company's invoices and are effective only upon purchase of products.
