



## **4983-BA-70 HIGH SOLIDS EPOXY ESTER RESIN**

**4983-BA-70 HIGH SOLIDS EPOXY ESTER RESIN** gives rapid set to touch and tack free times. Very good adhesion to metal surfaces and good chemical resistance.

### **SOLUTION PROPERTIES:**

Non-volatile by weight	70 ± 2%
Non-volatile by volume	65± 2%
Weight per gallon @ 25°C	8.19 ± 0.15 pounds
Viscosity @ 25°C	Z <sub>1</sub> - Z <sub>5</sub>
Flash Point (SETA)	81°F
Color (Gardner)	8 maximum
Solvent Present	n-Butyl Acetate
Cure Type	Air dry/force dry

### **SOLID RESIN PROPERTIES:**

Phthalic Anhydride	Absent
Oil Type	TOFA
Oil Length	Short
Acid Value	6 max.
Modifier	None
OH Equivalent Weight	N/A

### **DRIER RECOMMENDATIONS (% METAL BASED ON RESIN SOLIDS):**

0.05	-	0.08%	Cobalt
0.10	-	0.20%	Zirconium

April 2019

---

While the information contained herein is deemed accurate, it is intended as a guide only and property values and ranges listed above should be regarded as typical values and should not be construed either as a product specification or as a guaranteed analysis for any specific lot of the product. All guarantees/warranties and other terms existing are exclusively contained in the Company's invoices and are effective only upon purchase of products.

---