



## **5016-EP-70 WATER REDUCIBLE ACRYLIC MODIFIED ALKYD RESIN**

**5016-EP-70 WATER REDUCIBLE ACRYLIC MODIFIED ALKYD RESIN** at 70% non-volatile by weight in a mixed co-solvent system. It features a fast dry time and quick film hardness development and is formulated to give good exterior weathering, good initial gloss, and good gloss retention.

### **SOLUTION PROPERTIES:**

Non-volatile by weight	70 ± 1.0%
Non-volatile by volume	64 ± 1.0%
Weight per gallon @ 25°C	8.68 ± 0.15 pounds
Viscosity @ 25°C	Z <sub>3+</sub> - Z <sub>6+</sub>
Color (Gardner)	5 maximum
Solvent(s)	Isobutyl Alcohol/Glycol Ether EP/ Methyl Isobutyl Ketone
Flash Point (SETA)	62°F

### **SOLID RESIN PROPERTIES:**

Oil Type	Mixed Drying
Oil Length	Short
Acid Value	42-52
Modifier(s)	Acrylic

### **DRIER RECOMMENDATIONS:**

0.04	-	0.10%	Cobalt
0.04	-	0.08%	Zirconium

April 2019

---

While the information contained herein is deemed accurate, it is intended as a guide only and property values and ranges listed above should be regarded as typical values and should not be construed either as a product specification or as a guaranteed analysis for any specific lot of the product. All guarantees/warranties and other terms existing are exclusively contained in the Company's invoices and are effective only upon purchase of products.

---