



## **5075-BS-85 WATER REDUCIBLE SATURATED POLYESTER RESIN**

**5075-BS-85 WATER REDUCIBLE SATURATED POLYESTER RESIN** is a fast curing water reducible polyester resin intended for industrial and OEM finishes.

### **SOLUTION PROPERTIES:**

Non-volatile by weight	85 ± 1%
Non-volatile by volume	80 ± 1%
Viscosity @ 25°C	Z8 – Z8+
Weight per gallon @ 25°C	9.30 ± 0.15 pounds
Flash Point (Seta)	138°F
Color	4 Maximum
Solvent	2-Butoxy Ethanol/Sec-Butanol
Cure Type	Bake

### **SOLID RESIN PROPERTIES:**

Phthalic Anhydride	Absent
Modifier(s)	None
Acid Value	58 - 65
Oil Type	Oil Free
Oil Length	N.A.

### **DRIER RECOMMENDATION (% METAL BASED ON RESIN SOLIDS)**

None recommended...crosslink with melamine or urethane crosslinkers

April 2019

---

While the information contained herein is deemed accurate, it is intended as a guide only and property values and ranges listed above should be regarded as typical values and should not be construed either as a product specification or as a guaranteed analysis for any specific lot of the product. All guarantees/warranties and other terms existing are exclusively contained in the Company's invoices and are effective only upon purchase of products.

---